



Marie Magne
Sommer Needlepunch
341 rue de la Mairie
59780 BAISIEUX
FRANCE

Contact

e-mail

Original date

Didier Van Daele

FloorAndFire@ugent.be

29/01/2019

date

25/03/2021

TEST REPORT 19-0048-02

Translation of test report 19-0048-01 from 29/01/2019

Samples received

<u>Name</u>	<u>Date of receipt</u>
Flat needlepunched carpet with 100% synthetic fibre wear layer with impregnation based on latex SBR Commercial reference : ROCK / SP312 Production date: 10/01/2019 Mother bobbin: 180290361 Daughter bobbin: 190006724 OF1900611	15/01/2019

Aim of the test

Determination of the fire behaviour

Test conditions

Small flame test

Standard:

ISO 11925-2 (2010 + AC 2011)*

Method:

The use surface of a vertically put specimen placed (loose laid) on a fibre cement board (according to EN 13238) is ignited by a propane gas flame. Under condition of a surface flame attack with 15 s exposure time, there shall be no flame spread in excess of 150 mm vertically from the point of the test flame within 20 s from the time application.

If the boundary line is not reached within 20 s, the sample meets the requirements for the class E_{fl}.

Number of tests:

3 lengthwise and 3 crosswise

Conditioning

23 ± 2 °C and 50 ± 5 % R.H.

samples:

Fire Behaviour

Standard: **EN ISO 9239-1 (2010)***

Method: Before the test the samples are **not cleaned**.

A floorcovering is put on (**loose laid**) a fibre cement board (according to EN 13238). During the test, the specimen is irradiated by a gas radiator at an angle of 30°. A small flame is used to ignite the specimen. The specimen is ignited during 10 minutes. In case of inflammable specimens, the test lasts until the flame is extinguished, but 30 minutes at the most. The criterion is the burned length, from which the critical radiant flux is deduced using a calibration curve.

Number of tests: 4

Conditioning 23 ± 2 °C and 50 ± 5 % R.H.

samples:

The tests were finished in week 5/2019.

OBTAINED RESULTS

Small flame test

Ignition time : 15 s

Lengthwise


Sample	Burning time (s)	After glowing time (s)	Boundary line reached within 20 s
1	> 60 s	-	no
2	20 s	-	no
3	16 s	-	no

Crosswise

Sample	Burning time (s)	After glowing time (s)	Boundary line reached within 20 s
1	> 60 s	-	no
2	> 60 s	-	no
3	> 60 s	-	no

Fire behaviour

Specimen number	1 Length	2 Width	3 Width	4 Width	Average Specimens 2,3,4
Flame spread after 10 min (mm)	50	90	180	80	
Flame spread after 20 min (mm)	70	90	180	85	
Flame spread after 30 min (mm)	70	90	180	85	
Flame spread at extinction (mm)	70	90	180	85	
Flame time	12min 0s	12min 0s	12min 0s	12min 3s	
Critical heat flux CHF at extinction (kW/m ²)	10.9	10.7	9.5	10.8	≥11
Total smoke production at end of test (% min)	11	8	14	17	12



Didier Van Daele
Head of Floor covering and Fire Tests

ENCLOSURE TO REPORT 19-0048-02

*Classification according to EN 13501 –1 (2007 + A1: 2009)**

Classification	EN ISO 11925-2 (ignition time = 15 s)	EN ISO 9239-1 (test period = 30 min)	CLASS
B _{fl}	F _s ≤ 150 mm in 20 s	Critical flux ≥ 8.0 kW/m ²	X
C _{fl}	F _s ≤ 150 mm in 20 s	Critical flux ≥ 4.5 kW/m ²	
D _{fl}	F _s ≤ 150 mm in 20 s	Critical flux ≥ 3.0 kW/m ²	
E _{fl}	F _s ≤ 150 mm in 20 s	No demand	
F _{fl}	No demand	No demand	

*Additional classification smoke development according to EN 13501-1 (2007 + A1:2009)**

		CLASS
Smoke development ≤ 750%.min	s1	X
Smoke development > 750%.min	s2	